

TECHNICAL DATA SHEET



C200 HS EURO CLEAR



Packaging

5 Litre | PART# C200-5 | CASE QTY 4
1 Litre | PART# C200-1 | CASE QTY 6

Features

European 2:1 Clear with high gloss, good resistance to weathering and yellowing, good surface hardness and polishing properties. It is crystal clear.

Benefits

Provides high gloss and protection for basecoat.

Recommended Use

For painting passenger and commercial vehicles.

TECHNICAL DATA SHEET

Application: Total Respray/Blending In



For total re-spray apply 2 full coats observing flash off time of 8 – 10 minutes at 20°C between coats.

For spot blending: refer to blending-in topcoat Metallics / Solids

Drying Time



Tack-free

At 20°C: 8 hours
At 60°C: 25 – 30 mins
IR Short Wave: 7 mins
10 mins

Ready For Assembly

8 – 12 hours

Pot Life At 20°C:

3 hours

Remarks

Select hardener according to temperature and size of object to be painted.

TOUCANREFINISHES.COM

Logicar Inc. 1361 NW 155th Drive, Miami, FL 33169-5723, USA
Email us: sales@toucanrefinishes.com | Call us: 1-888-815-2278