







Features:	Toucan Refinishes Superlite Body-Filler B200 is made from the highest-quality raw materials. This lightweight filler is tack-free and creamy, so it's easy to spread and sand, making it perfect for steel surfaces of any size.																							
Substrates:	Bare Steel, Aluminum, Galvanized, Electro zinc-coated, Polyester surfaces, Epoxy primers																							
Mixing Ratio: 	100% by vol. Toucan Body Filler 2-3% by vol. Universal Cream Hardener	Part # B200																						
Application: 	Check the surface for moisture or contamination before filling. Spread the filler using a plastic or metal spreader, using slow, firm strokes and applying it in one direction.																							
Drying Times: 	At 20°C (68°F) 20 minutes At 60°C (140°F) 5 minutes																							
Surface Preparation: 	Remove rust from metal areas by sanding or sandblasting then clear the surface with a universal cleaner																							
Sanding:  	Dry sand with P 80-180 grit. Then use a guide coat and fine sand with P 220-240																							
Technical Data:	<table border="0"> <tr> <td>Specific Weight:</td> <td>9 lbs/gal at 20°C (68°F)</td> </tr> <tr> <td>Flash Point:</td> <td>90°F</td> </tr> <tr> <td>Solids Vol %:</td> <td>85%</td> </tr> <tr> <td>Solids Vol % (RTS):</td> <td>97%</td> </tr> <tr> <td>Coverage:</td> <td></td> </tr> <tr> <td>Viscosity (RTS):</td> <td></td> </tr> <tr> <td>Gloss:</td> <td>Matt</td> </tr> <tr> <td>Color:</td> <td>Grey</td> </tr> <tr> <td>V.O.C. Actual:</td> <td>1.58 lbs/gal (190 g/l)</td> </tr> <tr> <td>V.O.C. Regulatory RTS (less water, less exempts):</td> <td>0.35 lbs/gal (42 g/l)</td> </tr> <tr> <td>Applicable Use Category:</td> <td>Fillers & Putties</td> </tr> </table>		Specific Weight:	9 lbs/gal at 20°C (68°F)	Flash Point:	90°F	Solids Vol %:	85%	Solids Vol % (RTS):	97%	Coverage:		Viscosity (RTS):		Gloss:	Matt	Color:	Grey	V.O.C. Actual:	1.58 lbs/gal (190 g/l)	V.O.C. Regulatory RTS (less water, less exempts):	0.35 lbs/gal (42 g/l)	Applicable Use Category:	Fillers & Putties
Specific Weight:	9 lbs/gal at 20°C (68°F)																							
Flash Point:	90°F																							
Solids Vol %:	85%																							
Solids Vol % (RTS):	97%																							
Coverage:																								
Viscosity (RTS):																								
Gloss:	Matt																							
Color:	Grey																							
V.O.C. Actual:	1.58 lbs/gal (190 g/l)																							
V.O.C. Regulatory RTS (less water, less exempts):	0.35 lbs/gal (42 g/l)																							
Applicable Use Category:	Fillers & Putties																							
Pot Life at 20°C (68°F):	3-5 minutes once activated																							
Remarks:	The use of too much or too little hardener may lead to problems like poor adhesion, soft cure, and poor workability. Too much hardener may result in bleeding or staining. It must be isolated before applying finish coating. Polyester putties will not harden at temperatures under +40°F																							
Packaging:	Size: 3 L, 0.75 L																							